

102.14 - Nickel Oxides (powder form)

Technical Contact: thomas.vetter@nist.gov

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	Description	Unit of Issue	Si	Cu	Cr	Co	Ti	Al	Mg	Pb*	Se*	Bi*	As*	Sn*	Sb*	Cd*	Ga*
671	Nickel Oxide 1	25 g	0.047	0.20	0.025	0.31	0.024	0.009	0.030	16	2.0	0.07	(59)	(2.7)	(0.4)	(0.7)	(0.8)
672	Nickel Oxide 2	25 g	0.11	0.018	0.003	0.55	0.009	0.004	0.020	38	0.40	0.3	(74)	(4)	(0.5)	(1.7)	(0.4)
673	Nickel Oxide 3	25 g	0.006	0.002	0.0003	0.016	0.003	0.001	0.003	3.5	0.2	0.06	(0.4)	(((0.5)	(

Materials available in block form only

Absolute isotopic ratio

Conforms to National Committee for Clinical Laboratory Standards (NCCLS) specifications ACC-1

Components to be certified are yet to be determined.

Values in parentheses are not certified and are given for information only.

* Values are mg/kg.